La Metallurgia Italiana
International Journal of the Italian Association for Metallurgy

work rolls, but also to optimize rolling schedules. With applications of finite element method (FEM), the influences of the billet size, the reduction ratio, the friction coefficient, the rolling temperature and speed on the velocity and the distance of the relative sliding are investigated and compared between the flat and caliber rolling.

METHOD

Finite element simulation with a one quarter and non-isothermal model has been carried out for hot rolling using the software DEFORM™ 3D. The rectangular or the quadratic (Q) cross section of billets has a size ranging from 206 to 440 mm. The initial temperature difference between the surface and the center on the cross section is noted as T_d, as defined in Fig.1a. The flat roll has a diameter of 778 or 950 mm. The caliber roll has a box shape with a width of 251 mm at the top and a diameter of 778 mm. Both rolls rotate at a constant initial temperature and angle velocity.

Fig. 1 - a) Temperature distribution on the cross section. (b) v at the contact surface. (c) v at the contact node P1 vs. time. The area of the pointed zone is s for P1.

To evaluate the relative sliding, the mean value of the velocity and the total distance of the sliding in the contact region are employed. The relative sliding velocity (v) is defined as the mean difference in the velocity at the contact node between the billet and the roll, as shown in Fig.1b and 1c.

(1)

v_i is the velocity at the contact node, v_R the velocity of the roll, N the number of the contact nodes. The relative sliding distance (s) is the area of the velocity difference between the contact node and the roll, summed for all contact nodes in the contact region (Fig.1c for one contact node P1). s can be calculated as:

(2)

M is the number of the contact lines, k the number of the contact nodes (k>1) on each contact line, t the time step in the simulation. The reduction ratio is calculated with $H/H_0=(H_0-H_1)/H_0$. H_0 and H_1 are the billet height before and after rolling, respectively.